

<u>US LHC Accelerator Research Program</u> <u>bnl - fnal- lbnl - slac</u>

Technology development for Nb₃Sn long coils & magnets at Fermilab

Nikolai Andreev

LARP Collaboration Meeting 4 April 6 -8, 2005



Nb₃Sn long coil technology development

- Development goals
 - Demonstrate an industrial type of technology for coil production up to 4 meters long.
 - Fabricate, test and evaluate 2-layer shell-type coil design without internal interlayer splices
 - Fabricate, test and evaluate mechanical structures based on collaryoke-skin support
- Performance study:
 - magnet quench performance: training, re-training, SSL
 - field quality: geometrical harmonics, coil magnetization, iron saturation, alignment, field quality correction
 - quench protection: conductor parameters, quench heaters
 - operation margin: thermal model with mid-plane heaters



Nb₃Sn Dipole in Mirror Configuration – Cheapest Way for Long Coils Study.



Front view of Fermilab mirror magnet HFDM-04.


Mirror design uses a one half-coil and an iron half-cylinder as a magnetic mirror to produce the dipole field.

Advantages of mirror configuration:

- It minimizes conductor volume.
- It allows testing long shell-type coils
- It uses available coil winding and curing tooling (winding tables, mandrels, presses, etc.).
- Mechanical structure and tooling exist for 1-2 m long and for long up to 6 m long magnets.



TQa coil - Good Candidate for LARP Long Coil Study



Coil:

- 2-layer shell-type
- Inner-layer wedges
- Inner-layer pole glued into the coil


Cable:

- Strand Nb3Sn, 0.7 mm
- Number of strands 27
- Keystone angle 1 deg
- Width 10.05 mm
- Thickness 1.26 mm

Insulation: 0.125 mm.



TQ2a mechanical structure is available up to 6m long.



TQ2a cross-section

Modified MQXB collar blocks with outerlayer poles for coil alignment.

Radial yoke cut per lamination to provide symmetrical load.

Control spacers for collared coil alignment and yoke motion control.

Four shims in the midplanes to control coil-yoke interference.

The 10 mm thick stainless steel skin.

The coil pre-stress remains below 70MPa (100 MPa before the spring back) through all stages of magnet production and operation.



Cost Estimats

Cost estimates for shell-type TQ quad coils and shell-type HFDA dipole coils is summarized in Table

Parameter	TQa	TQa	Mirror	Mirror
Coil length, m	2	4	2	4
Cable cost, k\$	110	220	25	50
Coil & Magnet parts, k\$	115	160	12	42
Tooling modification, k\$	25	100	23	72
T&D Labor cost, k\$	450	550	144	173
Total cost, k\$	700	1,030	204	337

Cost of Long Furnace is not included.



Shell-type long coil program milestones

FΥ	'n	6
		()

-	Design of 2m long tooling:	FNAL	02/28/2006
-	Procure coil fabrication tooling/parts:	FNAL	04/30/2006
-	Fabricate insulated cable:	LBNL	04/20/2006
-	Fabricate practice coils:	FNAL+ LBNL	05/25/2006
-	Procure collars (modified from MQXB):	FNAL	05/15/2006
-	Assemble 2m mechanical model:	FNAL + LBNL	07/15/2006
-	Design of 4m long tooling:	FNAL	08/30/2006
-	Wind and cure 2m Nb ₃ Sn coils:	FNAL	08/25/2006
-	Procure and install long oven	FNAL	08/25/2006
-	React and impregnate coils:	FNAL	10/25/2006
FY07	7		
-	Assemble magnet:	FNAL + LBNL	01/15/2007
-	Test magnet:	BNL + FNAL	03/31/2007
-	Fabricate 4m practice coils:	FNAL+ LBNL	05/25/2007
-	Assemble 4 m mechanical model	FNAL	08/30/2007
-	Wind and cure 4m Nb3Sn coils	FNAL + LBNL	10/25/2007



Summary

- 1) Long TQa coils could be a base approach for long coil technology development.
- 2) Main tooling will be increased in length from 1-2m to 4m by connecting additional blocks. It is more effective way to upgrade tooling without wasting of a previous one.
- 3) Practice coils will be used to improve quality of procedures for coil production and magnet assembly.
- 4) Long Shell-type Coils & Magnet Program for FY2006-07 should be developed and approved in FY2005.
- 5) Long Shell-type Coils & Magnet Program at Fermilab should be started in FY2006.